

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

84-212321/34 C04 UAGR 17.09.82
UKR AGRIC ACAD *SU 1063-799-A
17.09.82-SU-496031 (30.12.83) C05c-01/02
Granulated ammonium nitrate stabilisation - involves using ferric salt
as iron-contg. additive

C(5-A3A, 5-B2A2, 5-B2A4, 5-C1, 5-C2, 12-M6, 12-M11, 12-N9) 7
0 8 1

C84-089103

The supplementary additive is polyphosphoric acid or ammonium polyphosphate. The ratio polyphosphate:ferric salts = 1:(0.1-0.5). The pref. ferric salt is nitrate, sulphate or citrate and the polyphosphate additive contains over 80% P205 in the polyanion. The ferric salt and polyphosphoric cpo. are pref. added at 1-4% on the wt. of ammonium nitrate. As previously, the stabilisation of granulated ammonium nitrate involves adding iron-contg. additive to its fusion.

USE/ADVANTAGE - to eliminate III/IV modified transitions and simultaneously improve physicochemical and agrochemical properties of the fertiliser, e.g. in agriculture.

Typically, the proposed method increases the economic efficiency by 3-5% (by reducing loss on storage, transport and application) and increases the mechanical strength (by 10 fold) and noncaking on storage. The prod. has high agrochemical properties. Bul.48/30.12.83. (3pp Dwg.No.0/0)